



Model Number: 9020

Harvard Chemical Wood Eze Based Urethane Topcoat Case 4-1 Gallon Bottles 9020

Manufacturer: Harvard Chemical Research

Harvard Chemical Wood Eze Waterborne Urethane Wood Finish Case

Restores, Protects, and Shines wood floors

When the convenience and simplicity of a one-part water based wood floor finish is in order, Wood Eze should be at the top of your list. The water based formula provides a gloss finish while it enhances the natural beauty of wood floors. Wood Eze wood floor finish provides excellent performance, strong durability and fast cure times.

31% Solids

Low VOC / no harsh fumes

Appearance: White liquid with low odor

pH: 8 to 9 Item# 9020

WOOD EZE

Water based urethane wood finish

DESCRIPTION

Wood-Eze is a water-based urethane dispersion wood finish that cures to a high gloss, durable and tough finish. Synthetic detergents and emulsifiers have little effect on this product's gloss and durability.

FEATURES

- User friendly
- Very low VOC
- Water based
- No flash point
- No harsh odors

INSTRUCTIONS

Previously Finished Floors:

PREPARATION:

1. Dust mop floor to remove dust, sand & debris.
2. Clean floor with Harvard Neutral Floor Cleaner. A previously sealed floor can be cleaned with an automatic scrubber.
3. Roughen and dull the old finish by using a single disc floor buffer (175 RPM) and a fresh black stripping pad or a 120-grit screen. One screen is required for every 500 sq. Feet (250 sq. ft. per side). Overlap each pass slightly to insure complete even coverage.
4. Mop the floor with Neutral Floor Cleaner then rinse until all dust and residue has been removed. Allow drying completely.

APPLY FINISH:

1. Using a clean synthetic applicator, apply thin, even coats with the grain of the wood.

Allow 1-hour dry time between coats. Humid conditions will necessitate longer dry time.

2. It is not always necessary to screen the first coat. If however, the grain has raised or the

coat has dried for longer than 4 hours, additional screening may be required. If so, screen

the floor with a previously used 120-grit screen or a fresh black stripping pad. Always vacuum and tack thoroughly after screening.

TIPS TO AVOID A BAD FINISH:

1. Turn air handlers off while applying Wood-Eze . You want to maintain a wet edge during

application. Air movement will adversely affect this edge. Block air movement from under

doorways with towels if necessary.

2. After application is complete, wait 10 minutes and turn air handlers on. 10 minutes should

be sufficient to allow top to skin over, reducing the possibility of any dust settling on to the

film. Air movement will enhance dry time.

SPECIFICATIONS

Appearance: Off white emulsion

Odor: Low

Specific gravity: 1.03

pH: 8.9

Flammable: No

Coverage: Up to 1000 sq. ft. per gallon, 1-2 hours recoat time and it cures in 24 hours.

Availability: This product was added to our catalog on Monday 12 December, 2016